

# 3M™ Bumpon™ Protective Products

## Resilient Rollstock - Clear Series

### SJ5600

### Product Description

3M™ Bumpon™ Protective Product SJ5600 series are resilient 70 durometer clear polyurethane rollstock products utilizing an aggressive acrylic-based, pressure sensitive adhesive. These products have a high strength acrylic adhesive that provides excellent shear properties at elevated temperatures. The adhesive adheres well to glass, many metal surfaces, some paints, and many high surface energy plastics (Formica®, ABS, polycarbonate, etc.). **Note:** This adhesive is not recommended for use on low surface energy plastics (polypropylene, polyethylene, etc.), or powdercoat painted and other various surfaces.

### Product Construction

Products	3M™ Bumpon™ Protective Products	
	SJ5632	SJ5616
<b>Material:</b>	Clear polyurethane	
<b>Release Liner:</b>	White 78.5 lb./ream silicone coated paper, printed 3M logo.	
<b>Adhesive:</b>	A-20 (acrylic)	
<b>Color:</b>	Transparent	
<b>Thickness:*</b>	1/32 in. 0.031 in. (0.8 mm)	1/16 in. 0.062 in. (1.6 mm)
<b>Thickness Tolerance: ± (inches) ± (mm)</b>	0.010 0.25	0.015 0.38
<b>Roll Length:</b>	72 yds.	36 yds.
<b>Roll Widths:</b>	4.5 in. (114.3 mm)	4.5 in. (114.3 mm)
<b>Slitting Tolerance: ± inches ± (mm)</b>	0.031 (0.8)	

\*ASTM-D-3767 procedure A (3.2 psi) measured without liner.

### Custom Rollstock Products

3M can customize thickness to your specifications. Call your 3M sales representative for details. Custom products require a minimum order quantity.

The thickness capability range for 3M™ Bumpon™ Resilient Rollstock SJ5600 series is 1/32 in. (0.031) minimum and 1/8 in. (0.125) maximum.



3M™ Bumpon™ Protective Products  
Resilient Rollstock - Clear Series  
SJ5600

## Typical Physical Properties and Performance Characteristics

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Property	Test Method	Test Results
<b>Hardness, Shore M:</b>	ASTM-D-2240	75
<b>Approximate Density, lb./ft.<sup>2</sup> (gm/cm<sup>3</sup>):</b>		70 (1.1)
<b>Resilience, %:</b>	ASTM-D-2632	6
<b>Kinetic Coefficient of Friction:*</b>	ASTM-D-1894 Glass, Stainless Steel Formica®	> 1 > 1
<p>*Two important laws of friction applicable to 3M™ Bumpon™ Protective Products Resilient Rollstock are (1) friction is independent of the area of contact between solids and (2) friction is proportional to the load between solids surfaces. Thus, if the load (weight) is doubled the force required to cause surface sliding is also doubled. This is expressed mathematically as follows:</p> <p style="text-align: center;">Slide force = (kinetic coefficient of friction) x (weight)</p>		
<b>Abrasion Resistance, gm/1000 cycles:</b>	ASTM-C-501; Tabor H, 1 kg	0.13
<b>Tensile, lb./in.<sup>2</sup> (kPa):</b>	ASTM-D-412, Die A	740 (5100)
<b>Elongation, %:</b>	ASTM-D-412, Die A	65
<b>Stain Resistance:**</b>	3M - 24 hrs. at 158°F against white paint, 7 days, 7 days exposed to UV	No staining
<b>Solvent Resistance:**</b>	3M - 24 hr. immersion 5% Detergent in water 25% Detergent in water 5% Bleach in water Gasoline Motor Oil Isopropyl Alcohol	No apparent effect No apparent effect No apparent effect Slight swelling No apparent effect Slight swelling
<b>Flammability Listing:</b>	Classification	UL94HB
<b>Load Tolerance:</b>	The "recommended" maximum load which 3M™ Bumpon™ Protective Product SJ5600 series rollstock will support is 100 psi (690 kPa) at 70°F (21°C) to 120°F (49°C).	
<b>Application Temperature:</b>	40°F (4°C) to 125°F (52°C)	
<b>Service Temperature:</b>	-30°F (-34°C) to 150°F (66°C); 225°F (107°C) intermittent exposure	

\*\* = Reference test for 24 hours only.  
Results may vary for different product application conditions.

# 3M™ Bumpon™ Protective Products Resilient Rollstock - Clear Series SJ5600

## Typical Adhesive Performance Characteristics

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### Static Shear Adhesive Performance

Temperature Tested at:	Time to Failure, minutes
75°F (24°C)	> 10,000
120°F (49°C)	> 10,000
158°F (70°C)	> 10,000
180°F (24°C)	> 10,000

One in. overlap shear test; ASTM-D-3654-M (1000 gram); testing completed on stainless steel test panels using 3M™ Bumpon™ Protective Product SJ5616.

### 90° Peel Adhesion Performance

Substrate	Peel Force, oz. per 1/2 in.
Polypropylene	3
Polystyrene	11
ABS	25
Stainless Steel	25
Aluminum	25
Glass	25

3M Test Method TM-2011; 72 hour dwell, 1/2 in. wide samples pulled at 12 in. per minute. Testing completed using Bumpon Protective Product SJ5616.

## Environmental Exposure

3M™ Bumpon™ Protective Products Resilient Rollstock Clear Series is intended for interior applications where resilience and all other physical properties will remain unchanged. When exposed to UV light for extended periods, some discoloration may occur. Bumpon clear rollstock may be used outdoors in a protected area with some discoloration possible. Simultaneous exposure to high humidity and temperature may degrade (soften) the product composition.

# 3M™ Bumpon™ Protective Products

## Resilient Rollstock - Clear Series

### SJ5600

## Features

- Transparent – universal color match.
- Excellent resistance to yellowing.
- Can be die cut to a variety of shapes and sizes.
- Good resistance (resulting from a urethane composition which contains no plasticizers) to marring or staining.
- Long aging resiliency – will not crack or harden.
- Excellent cushioning properties.
- Excellent abrasion resistance.
- Vibration and shock damping.
- Easy application – pressure sensitive adhesive backing.

## Application Ideas

- Die cut shapes for glass table tops, cushioning glass from metal and wood frames.
- Die cut shapes for use as cushions and spacers on cabinet doors, drawers, and lids.
- Die cut shapes for use as skid-resistant feet on small appliances and desk top equipment, hand held or desktop electronic devices.
- Die cut shapes for use as cushions and pads on glass or clear plastic shelves.
- Strips or pads for use as skid-resistant surfaces on glass or clear plastic shelves.
- Spacer or stop to prevent surface damage.
- Corner protection strips.
- Door kick pads.
- Anti-rattle spacer to fill gaps, dampen noise and reduce vibration.

## Application Techniques

To obtain maximum adhesion, surfaces must be unified, dry, and free of contaminants. Surface contact is fundamental to adhesive performance. To maximize contact on a substrate:

- Clean surfaces with low strength solvents such as isopropyl alcohol (rubbing alcohol) or heptane.  
**Note:** Be sure to follow the solvent's manufacturer's precautions and directions for use when using solvents.
- Apply firm pressure to increase the cold flow and contact of the adhesive with the substrate.
- Allow time (dwell) to increase the surface contact and adhesion.

**Note:** Product selection is ultimately the user's responsibility. Users should conduct their own tests under actual use and storage conditions to determine whether the product is fit for a particular purpose and method of application.

## Storage

Store in original cartons at 60-80°F (16-27°C) and 40-50% relative humidity.

## Shelf Life

To obtain best performance, use this product within 18 months from date of manufacture.

# 3M™ Bumpon™ Protective Products

## Resilient Rollstock - Clear Series

### SJ5600

## Certification/Recognition

**MSDS:** Refer to Product Label and Material Safety Data Sheet for Health and Safety Information before using this product.

**TSCA:** This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements.

**RoHS:** This product complies with the requirements of EU Directive 2002/95/EC and 2005/618/EC.

## For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-251-8634. Address correspondence to: 3M, Electronics Markets Materials Division, 3M Center, Building 225-3S-06, St. Paul, MN 55144-1000. Our fax number is 651-778-4244 or 1-877-369-2923. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

## Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

## Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



### Electronics Markets Materials Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
1-800-251-8634 phone  
651-778-4244 fax  
www.3M.com/Bumpons

3M and Bumpon are trademarks of  
3M Company.  
Formica is a registered trademark of  
the Formica Corporation.  
Please recycle. Printed in U.S.A.  
©3M 2012. All rights reserved.  
60-5002-0524-4

